


Ecofix Woodlook



5L 1L

As with all wood finishing always do a test area first to safeguard against an undesirable outcome. This technical data sheet is merely a guide and not a guarantee. All products are formulated to the best of our knowledge. The information is given as a result of many years experience. This product has had extensive tests carried out.

Produced by Debal Coatings nv

Industrieweg 29 - 8800 Beveren-
Roeselare Belgium tel. +32 (0) 51 30 11 40
fax +32 (0) 51 31 26 48
ciranova@ciranova.be

Versie / version : 01/2018

PRODUCT DESCRIPTION

Water based impregnation oil for parquet and wooden furniture
Ecofix woodlook bleaches the wood a bit so it retains longer it's original and untreated appearance. Particularly for interiors where a natural finish is needed such as parquet, veneer and other wooden objects.
Only for interior and domestic use. Only suitable for pale wood species.

TECHNICAL DATA

Viscosity	+/- 20 sec. (Din 4mm/20°C)
SOLID CONTENTS	+/- 26 % by weight
DENSITY	+/- 1,02 kg/lt.
Gloss	matt
NMP FREE	
CONFORM THE EUROPEAN DECO-PAINT DIRECTIVE 2010	

PREPARATION

Surface: Solid wood, ingeneerd wood. Sand the surface with grain 120 – 150 and afterwards remove sanding dust.

USER TIPS

ECOFIX Woodlook can be used both as a sealer and topcoat. Mix the product well before use. After mixing or stirring the product, the product has to rest for 15 minutes before use. Application is done by brush or roller. A short haired roller is preferred. Apply the first coat wet in wet to avoid overlap joints. When the first layer is dry, apply the second layer as the first layer. When the second layer is dry, sand with grain 150-180, remove sand dust and apply the third layer.



DRYING TIMES

Dust free: 20 to 30 minutes
Sandable: after 4 to 6 hours

The drying is strongly depending on the applied quantity, the temperature, air humidity and the ventilation of the room. Through a higher temperature and a good ventilation, drying time is limited.



APPLYING QUANTITY

12-15 m²/liter per coat.

AFTERTREATMENT

- Use Hard floor fresh Ciranova for regular maintenance.
- Use UNICARE X-MATT for periodic maintenance.
- Ecofix Woodlook can also be finished with OCULTO or FORTICO.

PRODUCT INFORMATION

Storage life: 12 months in original and unopened packing.
Warehousing at between 5°C and 40°C: not frost-durable.

SPECIAL QUALITIES

Use only stainless material. After use, since the material directly with water. This product cannot be poured into sewerage. If a stain on the wood is needed, only use AQUAPAD + hardener Ciranova. Be aware of discoloration or detachment because of wood compounds like resins or tannin.