

# CIRANOVA®


SINCE 1929

## TECHNICAL DATA SHEET

# Hardwaxoil Magic



5L 1L



As with all wood finishing always do a test area first to safeguard against an undesirable outcome. This technical data sheet is merely a guide and not a guarantee. All products are formulated to the best of our knowledge. The information is given as a result of many years experience. This product has had extensive tests carried out.

### Produced by Debal Coatings nv

Industrieweg 29 - 8800 Beveren-  
Roeselare Belgium tel. +32 (0) 51 30 11 40  
fax +32 (0) 51 31 26 48  
ciranova@ciranova.be

### PRODUCT DESCRIPTION

Flooring oil suitable for oil finishing of wooden floors. Good filling properties, natural colour, good chemical and mechanical resistance. Does not shine and is very matt. The durability can be improved by adding the hardener UA 5% (optional).

### TECHNICAL DATA

Viscosity +/- 35-45 sec. (Din 4mm/20°C)

SOLID CONTENTS +/- 47% by weight

DENSITY +/- 0,91 kg/lt.

GLOSS matt

#### COLOURS

**Standard:** natural, natural white, white, extra white, grey, old grey, smoked oak, black.

CONFORM THE EUROPEAN DECO-PAINT DIRECTIVE 2010

### PREPARATION

Sand the surface with grain 100 – 120 and afterwards remove sanding dust.

### USER TIPS

Before use, shake and stir well. Can be applied by polishing machine (white or beige pad), paintbrush, roller or cloth. After applying the oil, the excess has to be buffed in until the surface doesn't feel sticky. At least 2 coats are recommended for hard wood such as oak. For soft wood multiple coats can be applied.

For industrial use, please contact our service centre.

TIP: an oil retarder Ciranova can be added to extend the open time.



### DRYING TIMES

Hardwaxoil MAGIC NATURAL: +/- 6 hours.

COLORED Hardwaxoil MAGIC: +/- 12 hours

The drying time is strongly depending on the applied quantity, the temperature and the ventilation of the room. Through a higher temperature and a good ventilation, drying time is reduced.



### APPLYING QUANTITY

40-50 m<sup>2</sup>/liter per coat

### AFTER TREATMENT

Clean regularly with flooringsoap Ciranova. Depending on the use of the floor, use maintenance oil 1 time a year. For thorough cleaning, use Intensive Cleaner Ciranova®.

ATTENTION: The hardwaxoil needs +/- 14 days to fully cure. Don't use any water or maintenance products on the floor during this period.

### PRODUCT INFORMATION

Shelf life: up to 2 year in a well closed original packaging.

### SPECIAL QUALITIES

Used cloths or pads should be plunged in water because of the danger of spontaneous combustion.

We recommend Hardwaxoil Magic Natural as topcoat on the pigmented Hardwaxoils.

Hardwaxoil Magic Natural and Natural White can be used as a primer to isolate the water borne Ciranova stains, so it can be overcoated with a waterbased Ciranova lacquer.

**Colored Hardwaxoils should always be tested before treating the entire surface.**

**Used sanding grain, type of wood, ..... may affect the final colour.**